

TEROSON PU 8630 HMLC

June 2019

Adhesive with high shear modulus and low conductivity

PRODUCT DESCRIPTION

Technology	2K- Polyurethane adhesive free from PVC and solvents
Product Type	Direct Glazing Final strength after approx. 5 h
In driving condition with airbag	1 hour after the window has been bonded (Crash-Norm: FMVSS 208 / 212 (50 km/h, 100% frontal)) 2 hours after the window has been bonded (European Crash Standard (64 km/h, 40% overlap))

The direct glazing adhesive is outstanding for the following properties:

- Very good sag resistance
- High elastic and shear strength, even after aging
- Very low conductivity
- Good adhesion to the remaining material
- High shear modulus
- High UV resistance in connection with primer/activator
- Excellent adhesion to glass, glass with the ceramic coating, encapsulation and to painted surfaces, in connection with primer/activator
- Easy to use (application with battery gun / 1C pneumatic gun)

Application Areas:

TEROSON PU 8630 HMLC is used for the bonding of front, rear and side screens to the body of motor-, utility-, special- and rail vehicles.

TECHNICAL DATA

(Typical Test Results)

Colour:	black
Odour:	weak
Consistency:	smooth, sag-resistant, pasty
Density g/cm ³ :	approx. 1.2
Solids:	100 %
Shore-A-hardness: (DIN 53505)	approx. 60
Tensile strength: (DIN 53504)	approx. 9.5 MPa
Stress: (DIN 53504)	approx. 5.7 MPa at 100 % elongation
Shear modulus: (according to DIN 54451)	approx. 3.0 MPa
Elongation at break: (DIN 53504)	approx. 370 %
Shear strength: Layer thickness 5mm based	4 to 5 MPa (fully cured)

on DIN 54451

Specific forward resistance: (ASTM D 257-99 / DIN IEC 60093) approx. 1×10^{10} Ω cm

Volume change: (DIN 52451) < 1 %

Glazing time*: max. 25 min

Material application temperature, °C: 60 to 70

In service temperature range, °C: -40 to 90

Short exposure (up to 1 h), °C: 120

* period of time between beginning of material application until inserting of the pane

Surface Preparation:

The substrates to be bonded must be dry and free from oil, dust, grease and other contaminations. Check new glass if it is correct and free of any damage. To obtain an optimal adhesion on the new screen we recommend 2 different surface preparation methods (solvent based, TEROSON VR 10 or waterborne, TEROSON VR 100):

1. Wipe off surface with a lint free cloth and TEROSON VR 10.
2. Abrade bondline with a smooth abrasive pad or wetted TEROSON ET Cleaning sponge.
3. Wipe off again surface with a lint free cloth and TEROSON VR 10.

Or

1. Spray on TEROSON VR 100 on the to be cleaned surface.
2. Abrade wetted bondline with TEROSON ET Cleaning sponge.
3. Dry off the bondline by wiping in one direction using a lint free cloth.

Evaporation time for both methods: 2 minutes.

Cleaning of the cut adhesive layer, remaining on the window aperture, is in general not necessary.

If, however, cleaning of this remaining layer is indispensable, an evaporation time of at least 5 minutes is mandatory.

Priming:

With the use of an applicator apply a thin layer of All-in-one primer TEROSON PU 8519P to the cleaned substrate surface.

Ensure the wet film should be 0.025 mm.

Let the primed surface evaporate for approx. 15 minutes before the direct glazing sealant is applied.

If a fresh bonding is made directly on the remaining material layer (left in the window cut-out of the body), this layer should not be primed within the first 2 hours after cutting back. But if the remaining layer is not used within the first 2 hours, it has to be activated with TEROSON PU 8519P. Provided that it is not contaminated with dust or grease, the remaining layer is the best adhesive surface, if TEROSON PU 8630 HMLC is used for the new bond.

If windows are bonded which have been pre-coated with a primer or PUR-based adhesive/sealant by the glass supplier, the primer TEROSON PU 8519P is also suitable to ensure the correct adherence of TEROSON PU 8630 HMLC to the pre-coating.

By means of an applicator, a thin layer of TEROSON PU 8519P is applied to the pre-coating. Following this, an evaporation time of approx. 15 minutes has to be observed. Subsequently, TEROSON PU 8630 HMLC is applied as usual, but taking into consideration the layer thickness of the pre-coating.

Processing:

Prior to its use, the cartridge containing the A-component of TEROSON PU 8630 HMLC must be warmed in the TEROSON cartridge warming box for at least 30 minutes, resp. 60 minutes in the pre-heating box for cartridges and foil packs. Immediately before the application, the B-component is fully screwed onto the opened cartridge. Then processing is carried out using a battery driven gun or a compressed-air pistol with a piston rod.

Recommended tools:

TEROSON PoweLinell ; working pressure: 8 to 10 bar

Application should be performed in one step. Extrusion time for a complete cartridge should be between 90 to 120 seconds to achieve the best performance.

Preliminary Statement:

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification

Transport information

Regulatory information

Storage:

Frost sensitive	yes
Recommended storage temperature	5 to 25 °C
Shelf life	12 months aluminium cartridge

ADDITIONAL INFORMATION**Disclaimer:****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 2